

7. The process as claimed in Claim 6, wherein said water soluble, non-hydrating inorganic material is the double salt $\text{Na}_2\text{SO}_4:\text{Na}_2\text{CO}_3$ in a weight ratio of Na_2SO_4 to Na_2CO_3 of from 80:20 to 20:80.

a) 8. The process as claimed in Claim 7 wherein said step of providing said aqueous coating solution further is characterized by the step of spraying said coating solution into said coating mixer.

9. The process as claimed in Claim 8 wherein said coating mixer is a fluidized bed having a disengagement plane and said coating solution is sprayed into said fluidized bed from above said disengagement plane.

09914527 082901